

**Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently amended) A method of producing a magnetic recording medium comprising

providing a nonmagnetic substrate;

forming a metal underlayer formed of Cr or a Cr alloy on said substrate;

forming a ferromagnetic metal layer, wherein said ferromagnetic metal layer contains a plurality of ferromagnetic films and a nonmagnetic metal spacer layer formed between said ferromagnetic films, wherein the step of forming said ferromagnetic metal layer is a step of forming alternately a plurality of ferromagnetic films and one or more nonmagnetic metal spacer layer or layers in a multilayer, and

allowing at least the interface between said nonmagnetic metal spacer layer or layers and said ferromagnetic films to adsorb physically oxygen and/or nitrogen

wherein the gas used for forming said nonmagnetic metal spacer layer or layers is a mixed gas obtained by mixing oxygen or nitrogen with Ar or other rare gases and the partial pressure of oxygen or nitrogen contained in such mixed gas is set at  $3 \times 10^{-6}$  Torr or above and  $3 \times 10^{-6}$  Torr or below.

2. (Currently amended) The method of producing the magnetic recording medium according to claim 1 wherein said nonmagnetic metal spacer layer or layers is or are formed in such a way that said oxygen and/or nitrogen ~~may be~~ is contained in the film of the nonmagnetic metal spacer layer or layers.

3-5. canceled.

6. (Previously presented) The method of producing the magnetic recording medium according to claim 1 wherein the step of allowing at least the interface between said nonmagnetic metal spacer layer or layers and said ferromagnetic film to adsorb physically oxygen and or nitrogen is a step of exposing the surface of said nonmagnetic metal spacer layer or layers to an atmosphere containing oxygen and/or nitrogen.

7. (Original) The method of producing the magnetic recording medium according to claim 6 wherein the exposure of the surface of said nonmagnetic metal spacer layer or layers to oxygen is set at 10 Langmuir or more.

8. (Previously presented) The method of producing the magnetic recording medium according to claim 1 wherein a metal film containing a kind or more of element or elements chosen from Ru, Ir, Cu and Os for said nonmagnetic metal spacer layer or layers is formed.

9. (Previously presented) The method of producing the magnetic recording medium according to claim 1 wherein the thickness of said nonmagnetic metal spacer layer or layers is set at 0.5 nm or more and 1.0 nm or below.

10-18. (Canceled).

19. (Currently amended) A method of producing a magnetic recording medium comprising

providing a nonmagnetic substrate;

forming a metal underlayer formed of Cr or a Cr alloy on said substrate;

forming a ferromagnetic metal layer, wherein said ferromagnetic metal layer contains a plurality of ferromagnetic films and a nonmagnetic metal spacer layer formed between said ferromagnetic films, wherein the step of forming said ferromagnetic metal layer is a step of forming alternately a plurality of ferromagnetic films and one or more nonmagnetic metal spacer layer or layers in a multilayer, and

allowing all interfaces between said nonmagnetic metal spacer layer or layers and said ferromagnetic films to adsorb physically oxygen and/or nitrogen

wherein the gas used for forming said nonmagnetic metal spacer layer or layers is a mixed gas obtained by mixing oxygen or nitrogen with Ar or other rare gases and the partial pressure of oxygen or nitrogen contained in such mixed gas is set at  $3 \times 10^{-6}$  Torr or above and  $3 \times 10^{-5}$  Torr or below.

20. (New) The method of producing the magnetic recording medium according to claim 1, wherein said ferromagnetic films adsorb physically nitrogen.

21. (New) The method of producing the magnetic recording medium according to claim 19, wherein said ferromagnetic films adsorb physically nitrogen.